



STANDARD SPECIFICATION
ALUMINUM L-FOOT FINNED TUBES
(SOLID & PERFORATED FIN)

(Effective October 15, 2013)

Vulcan Finned Tubes, L.P.
27951 Commercial Park Drive
Tomball, Texas 77375

Phone: 281-255-4775
877-466-0055 (toll free)
Fax: 281-516-7878

www.vulcanfinnedtubes.com

VULCAN FINNED TUBES, L.P.
STANDARD SPECIFICATION
ALUMINUM L-FOOT FINNED TUBES
(SOLID & PERFORATED FINS)

1.0 SCOPE

- 1.1 This specification governs materials, fabrication and tolerances (where required) applicable to aluminum L-foot finned tubes fabricated by Vulcan Finned Tubes, L.P. ("Vulcan").

2.0 ORDERING INFORMATION

- 2.1 The purchaser is responsible for specifying all information necessary for ordering the required materials.
- 2.2 Tube material information will include quantity, tube specification, OD and wall thickness, over-all tube length and tube end preparation.
- 2.3 Fin material information will include fin specification, fin height, number of fins per inch, length of finned length and length of tube bare ends.

3.0 TUBE SPECIFICATIONS

- 3.1 The tube may be supplied by the purchaser or by Vulcan, as agreed between the two parties.
- 3.2 If purchaser supplies the tubes, they must send mill test reports with the tube material. Mill test reports or other acceptable manufacturer's certification shall be provided to the purchaser for all tubes supplied by Vulcan.
- 3.3 The tube's chemical and physical characteristics shall be per the specification chosen by the purchaser unless otherwise specified.
- 3.4 Standard outside tube diameters shall be 5/8", 3/4", 1", 1-1/4" or 1-1/2" as specified.
- 3.5 To be suitable for finning, tubes must be straight and the tube outside surface must be free from any pitting, dents or other surface defects that would interfere with the application of the fin.

3.6 Length tolerance for tubes cut to length by Vulcan shall be as follows:

Tube Length	Plus Tolerance	Minus Tolerance
Less than 24 ft.	.125 in.	.125 in.
Greater than 24 ft.	.25 in.	.125 in.

3.9 Tube end preparation shall be square-cut and deburred.

4.0 FIN STRIP SPECIFICATIONS

4.1 Vulcan shall supply fin strip material.

4.2 The fin strip material shall be aluminum 1100-0 or aluminum 5005 as specified by purchaser.

4.3 If requested by customer at time of order, Vulcan shall furnish mill test reports or other acceptable manufacturer's certification for fin strip materials.

4.4 Standard fin heights shall be 3/8", 7/16", 1/2" or 5/8" as specified by purchaser.

4.5 Fin strip thickness shall be .015 in. (+/- .001 in.) thick before being formed tension wound around tube.

4.6 Standard fin pitch is 8 to 12 fins per inch with 10 fins per inch being most commonly purchased.

5.0 FABRICATION

5.1 Tubes are not required to be cleaned prior to finning unless otherwise specified.

5.2 The base of the fin is formed into a L-foot shape and wound helically around the outside diameter of the tube forming a mechanical bond between tube and fin. Two galvanized staples shall secure each finned end.

5.3 Fins shall be solid or perforated as specified by purchaser.

5.4 Fin attachment shall be secure over the entire tube length.

5.5 The cup of the fin shall be uniform throughout the entire tube length.

5.6 Fin splices are permissible, providing there are no splices within 10 ft. of another and tubes with splices do not account for more than 10 percent of the total order.

5.7 Fin outside diameter tolerances shall be +0, -.015" unless otherwise specified.

5.8 The number of fins per inch shall be as specified +/- 5 percent as determined on not less than 12 in. of finned length.

5.9 Finished finned tubes shall be straight with a maximum deviation of .25 in. in any 10 ft. section of tube.

6.0 INSPECTION

6.1 Upon receipt at Vulcan's shop, tubes shall be visually inspected to verify dimensions and material specification and to ensure no obvious defects. Tube material having any defects that may effect weld quality will not be used.

6.2 Prior to production, fin material shall be visually inspected to verify dimensions and material specification and to ensure no obvious defects. Fin material having any defects will not be used.

6.3 All finned tubes shall be visually inspected during the finning process and once again prior to packaging and shipping. All finned tubes shall have a workmanlike finish and be free from obvious defects.

7.0 PRODUCT PACKAGING

7.1 Standard packaging options are fully enclosed steel-banded wooden crates. Other options such as export quality crating and fumigation can be provided upon request.